

Technical Datasheet

Create Date: 17.11.2017 - Seite 1/3

Easy-Mix N 5000 Epoxy Adhesive



almost colourless/crystal clear liquid, self-levelling shorter pot life

Easy-Mix N 5000 is transparent, liquid, self-levelling, has a pot life of 20 minutes and a high adhesive strength.

It can be used for many materials, such as metal, plastic, fiber composites, ceramic, glass, stone and wood. It is suited for connections where a transparate bond is important.

Technical Data

Base	Epoxy resin unfilled
Composition	liquid
Colour	almost colourless, glass clear
Mixing ratio by weight (Resin / Hardener)	1:1
Density of the mixture	1,07 g/cm ³
Viscosity of the mixture at 20°C (+68°F)	5.000 mPa·s
Adhesive gap bridging up to max.	2 mm
Processing temperatur	+10 to +35 °C
Curing temperature	+6 to +40 °C
Pot-life at 20°C (+68°F) for 10ml material	20 min.
Handling strength (35% strength) after	60 min.
Capable of bearing mechanical loads (50% strength) after	r 3 h
Final strength (100%) after	48 h
Medium strength of the pure epoxy resin according to DIN	N 53281-83
Pressure	10 Mpa
Pull	40 Mpa

Bending	50 Mpa
E-Modul	1.700 - 2.000 Mpa
Shore hardness D	65
Medium shear strength according to DIN 53283 at	
Steel sand blasted	21 N/mm²
Alu sandblasted	19 N/mm²
PVC hard-roughened	14 N/mm²
Linear shrinkage	2,0 %
Temperature resistance	-50 to 100 °C

Surface pre-treatment

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using WEICON Surface Cleaner).

Processing

WEICON Easy-Mix products can be processed directly from the double cartridges with the help of the included static mixer. Reject the first 5 cm of the dosed bead. Apply adhesive to only one of the surfaces to be bonded. The pot life given is for a material quantity of 10 ml at room temperature. If larger quantities are used, the curing time will be faster. Similarly, higher ambient temperatures shorten the cure times (as a rule of thumb, every +10°C increase above room temperature will halve working and curing time). Temperatures below +16°C will extend working and curing times considerably, while below about +5°C, no reaction will take place at all.

Storage

When kept at a constant room temperature of about +20°C and unopened in dry conditions, WEICON Epoxy Adhesives will keep for at least 18 months. Avoid direct sunlight. If these storage instructions are disregarded, the storage life will be reduced to 6 months. Epoxy resins are fundamentally liable to crystallise at temperatures of less than +5°C. This effect is accentuated by wide variations in temperature such as can frequently occur during transport in winter. This also has a negative effect on working qualities, curing and technical details, although these effects can be reversed by warming up to a maximum of +50°C (no naked flame). In the case of WEICON Epoxy Adhesives, careful selection and combination of the base resins (bisphenol A and F) ensures a reduction of crystallisation.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10650250

Easy-Mix N 5000 Epoxy Adhesive 50 ml

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com



Technical Datasheet

Accessories:

10650005 Mixing Nozzles Easy-Mix, Quadro

10653050 Dispenser D 50,

11202400 Sealant and Adhesive Remover, 400 ml

11207400 Surface Cleaner, 400 ml 11850200 Hand Protective Foam, 200 ml 12955175 Dosing Tips, Typ A Size 0,5

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.