

RITE-LOK Cyanoacrylate Adhesive PR1500

Product Data Sheet

Updated : February 2007
Supersedes : New

Product Description RITE-LOK PR1500 is a high viscosity (1500 cPs) Ethyl Cyanoacrylate based adhesive. PR1500 is formulated for rapid, high strength bonding of plastics and rubbers but is also suitable for bonding a very wide range of materials.

Key Features PR1500 is specially formulated for high strength, general purpose bonding of most plastics and rubbers. PR1500 has excellent gap-filling ability and can be used on parts that do not fit together perfectly. The high viscosity formulation means that the adhesive does not wick in unwanted areas.

Physical Properties	Base	Ethyl
	Soluble In	Acetone, MEK
	Viscosity (cps)	Range 1275-1650 Typical Value 1500
	Specific Gravity	1.08
	Colour	Clear

Performance Characteristics	Maximum Gap Fill (best results are obtained with very thin bond lines)	0.2mm
	Fixture Time	20-100
	Tensile Strength (ISO 6922)	20 N/mm ²
	Full Cure	24hrs
	Speed of Cure	The speed of cure of cyanoacrylates varies according to the substrate to be bonded. Acidic surfaces such as paper and leather will have longer cure times than most plastics and rubbers.
	Moisture Resistance	Low resistance to high levels of moisture and humidity over time.
	Service Temperature Range	-50 to +80°C

Date: February 2007

Additional Product Information	RITE-LOK Activators AC11 and AC12 may be used in conjunction with RITE-LOK cyanoacrylates where cure speed needs to be accelerated. Cure speeds of less than 2 seconds can be obtained with most RITE-LOK cyanoacrylates. The use of an activator can reduce the final bond strength by up to 30%.
Application Techniques	<p>Bond speed is very fast so ensure that parts are properly aligned before bonding. RITE-LOK Activators may be required if there are gaps or porous surfaces. Some plastics may require application of RITE-LOK AC77 Primer.</p> <p>Ensure parts are clean, dry and free from oil and grease. Product is normally hand applied from the bottle. Apply sparingly to one surface and press parts firmly together until handling strength is achieved.</p> <p>As a general rule, as little cyanoacrylate as possible should be used – over application will result in slow cure speed and lower bond strength.</p>
Storage Conditions	<p>Keep the adhesive in a cool, dry place away from direct sunlight. Under such conditions shelf life at room temperature will be 12 months.</p> <p>Refrigeration to 5°C gives optimum storage stability.</p>

Shelf Life	12 months from date of despatch when stored in the original carton at 21°C
-------------------	--

Precautionary Information	Refer to product label and material Safety Data Sheet for health and safety information before using the product.
----------------------------------	---

Product Use	All statements, technical information and recommendations contained in this document are based upon tests or experience that are reliable. However, many factors beyond control can affect the use and performance of a product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and suitable the user's method or application.
--------------------	--

Note	<p>Values presented have been determined by standard test methods and are average values not to be used for specification purposes.</p> <p>Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendation</p>
-------------	---