

# AL-F High Performance Grease



## Available sizes:

26550035	AL-F High Performance Grease 350 g
26550040	AL-F High Performance Grease 400 g
26550100	AL-F High Performance Grease 1.0 kg
26550500	AL-F High Performance Grease 5.0 kg
26550925	AL-F High Performance Grease 25.0 kg

## Accessories:

10953001	Processing Spatula, short
10953003	Processing Spatula, long

## Allround High Performance Grease NSF approval

WEICON AL-F can be used to lubricate rolling and sliding bearings, joints, levers, sliding guides, spindles, spline shafts, camshafts, open gears, worm gears and all grease lubrication points, even in the food industry.



## Technical Data

Abbreviation (DIN 51502)	KLF 2K -30
Consistency assignment (DIN 51818)	NLGI-Class 2
Composition	Lithium soap / mineral oil
Colour	white
Conforms to	NSF-H 2, LFGB Section 31 and Section 5
Temperature resistance	-30 to +120 °C
ISSA-Code	53.052.30/31

## Surface pre-treatment

Clean surfaces.

## Processing

Apply AL-F evenly.

## Storage

Keep in closed original container. Do not store together with oxidizing agents. Keep container tightly closed and store at cool and ventilated place. Recommended storage temperature: room temperature.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

		AL-F
Abbreviation (DIN 51502):		KLF 2K -30
Consistency assignment (DIN 51818):		NLGI-Class 2
Basis:		Lithium soap / mineral oil
Colour:		white
VKA Test (DIN 51 350):	welding load	3600 N
	goods load	3400 N
	Spherical cap value (1 Min / 1000 N)	0,8 mm
Speed identifying value ( $k_a \cdot n \cdot d_m$ ):		350 000
Worked penetration (DIN ISO 2137):		280 ± 15 1/10 mm
Water resistance (DIN 51807):		1 - 90
Temperature resistance		-30°C to +120°C (-22 to +248°F)
Drop point (IP 396):		>190°C (+374°F)
Kinematic viscosity (DIN 51 562):	+40°C (+104°F)	approx. 100 mm²/s
	+100°C (+212°F)	approx. 9 mm²/s
Salt spray test with separated protective coats (Federal German Armed Forces Regulations 336 h/35°C, 5% NaCl):		---
EMCOR-corrosion test (DIN 51 802):		0 / 0
Density at +20°C (+68°F) (DIN 51757):		0,90 g/cm³
Conforms to:		NSF-H 2
Shelf life at least (months)*:		24

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weiconcz.cz

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com