

Easy-Mix PE-PP 50 Structural Acrylic Adhesive



transparent | for low surface energy plastics | for small bonding gaps

WEICON Easy-Mix PE-PP 50 is a 2-component construction adhesive based on methyl acrylate. Due to its transparent curing, it is particularly suitable for visually appealing, high-strength adhesive bonding of low surface energy plastics, such as PE, PP and TPE. Thanks to its special formula, the adhesive is suitable for zero-gap bonds and for connecting surfaces with extremely small bonding gaps of less than 0,2 mm. The structural adhesive has a fast strength build-up and a high final strength. It is impact-resistant, ageing-resistant, chemical-resistant, and slightly thixotropic. PE-PP 50 has a short pot life of six minutes and a processing time of twelve minutes. It is applied with a 1:1 system and does not require pre-treatment of the bonding surfaces, as the adhesive has an integrated primer. For the application of the Easy-Mix product, the Dispenser Easy-Mix D 50 is required.

Characteristics

Base	methyl methacrylate
Texture	pasty

Processing

Processing procedure	Easy-Mix
Mixing ratio by weight	1:1
Viscosity of the mixture	20.000 mPa·s
Density of the mixture	1 g/cm ³
Gap bridging up to max.	0 - 1,00 mm

Curing

Pot life	at 20 °C	6 min.
Handling strength	(35 % strength)	12 min.
Final strength	(100 % strength)	24 h

Mechanical properties after curing

Lap shear strength material thickn. 1,5mm DIN EN 1465	
Steel 1.0338 sandblasted	12 N/mm ²
Stainless steel V2A sandblasted	11 N/mm ²
Aluminium sandblasted	12 N/mm ²
Galvanized steel	7 N/mm ²
PVC-rigid roughened	12 N/mm ²
CFRP	12 N/mm ²
ABS	3 N/mm ²
PC (polycarbonate)	6 N/mm ²
GFRP	15 N/mm ²
PMMA	8 N/mm ²
Polyamide 6.6	2 N/mm ²
PE-HD	12 N/mm ²
PP (polypropylene)	8 N/mm ²

Thermal parameters

Temperature resistance	-50 °C to +80 °C, briefly up to +100 °C
------------------------	---

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface pre-treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner). Smooth surfaces can be roughened mechanically.

Processing

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side. The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5C and below, no reaction takes place.

Storage

12 months at +2°C to +7°C, 3 months at +20°C to +25°C

Accessories

- 10653050 Dispenser Easy-Mix D 50, 1 PCE
- 10650005 Quadro Mixing Nozzle, 1 PCE

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Easy-Mix PE-PP 50 Structural Acrylic Adhesive

Structural Acrylic Adhesives

PE-PP

Conversion table

$(^{\circ}\text{C} \times 1,8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8,851 = \text{lb}\cdot\text{in}$
$\text{mm}/25,4 = \text{inch}$	$\text{Nm} \times 0,738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25,4 = \text{mil}$	$\text{Nm} \times 141,62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0,225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0,571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25,4 = \text{V}/\text{mil}$

Available sizes:

10665050 Easy-Mix PE-PP 50 Structural Acrylic Adhesive, 50 ml

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr