

Chrome-Silver Spray



high-brilliance anticorrosive surface coating on aluminium

Chrome-Silver Spray is a high-brilliance surface coating. The special formulation and highest purity of the metal pigments create a high gloss finish.

WEICON Chrome-Silver Spray can be used for prototypes and samples, mirror applications (e.g. reflectors), trade show and exhibition construction, effective decorative work and for the optical refinement of the most diverse materials.

Technical Data

Colour	aluminium, glossy
Application range	inside
Silicone free	yes
Binding agent	natural resin
Pigment	flaky aluminium pigments
Pigment purity	approx. 99,5% Al
Percentage of metal in dry film	15 %
Specific weight	0,8 - 0,9 g/cm ³
Recommended primer	Zinc-Spray
Processing temperature	+5 to +35, optimal +18 to +35 °C
Consumption at 1.5 cross coats	150 ml/m²
Layer thickness at 1.5 cross coats	10 -20 μm
Dust dry after	10 min.
Hardened after	4 -6 h
Abrasion-resistant yes/no	not abrasion-resistant
Cross cutting DIN 53151/ ISO 2409	cross cut characteristic value GT 0 to GT 1
Mandrel bend test DIN EN ISO 1519	no hair cracking
Top coating	not required
Storage stability	24 months
Temperature resistance	-50 to +400 °C

Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20°C) and at about 25 cm distance from the surface. Dust-dry after approx. 10 minutes, fully hardened after approx. 4-6 hours.

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50°C.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

11103400 Chrome-Silver Spray 400 ml

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG Germany phone +49 (0) 251 9322 0 info@weicon.de www.weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za www.weicon.co.za

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae www.weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 www.weicon.com.sg

WEICON Inc Canada phone +1 877 620 8889 www.weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 www.weicon.es

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com www.weicon.com.ro

WEICON Italia S.r.I. Italy phone (+39) 0102924871 www.weicon.it